

July 3, 2001
Date

Dail Gaman
Express Mail Label No.:
EL 846221549 US

a

~~LIQUID CRYSTAL DISPLAY DEVICE AND~~
~~PRODUCTION METHOD THEREOF~~

BACKGROUND OF THE INVENTION

Field of the Invention

This invention relates to a liquid crystal display device of an MVA mode that controls an alignment direction of liquid crystal molecules by utilizing protrusive structures disposed on a substrate surface or non-electrode regions (slits) of each transparent pixel electrode, and a liquid crystal display device that regulates an alignment direction of liquid crystal molecules by using a photo-cured product formed of a photo-curing composition having a liquid crystal skeletal structure.

Description of the Related Art

A liquid crystal display device has been utilized not only for mobile application such as notebook type personal computers and portable information terminals but also for desktop type computers and television monitors to satisfy social requirements for space saving and energy saving. Performance of the liquid crystal display device has been drawn into comparison with that of CRT monitors. Development has been made to improve performance of the liquid crystal display device to the level of performance of the CRT monitors.

The CRT monitor makes use of light emission of a fluorescent material and has low angle dependence. Its viewing angle is wide. On the other hand, the liquid crystal display device electrically controls alignment directions of the liquid crystal molecules when the rays of light from a light source transmit through a liquid crystal layer to change a transmission and to display images. Even though contrast in a vertical

0909340-070304

direction to a screen can be satisfied, the liquid crystal display device has large viewing angle dependence such that contrast is small when viewed from an oblique direction and chromatic inversion develops.

For example, a liquid crystal display device of a twisted nematic (TN) mode, in which molecules of a liquid crystal material having positive dielectric anisotropy is arranged horizontally to a substrate surface and is twisted 90 degrees between opposing substrates, has been widely utilized as a liquid crystal display (LCD) using an active matrix. The greatest drawback of this TN mode LCD is that the viewing angle is small. Various studies have therefore been made to improve this viewing angle characteristic.

For example, an MVA (Multi-domain Vertical Alignment) mode is known that divides one pixel into multiple domains and disperses the alignment direction for each domain to enlarge the viewing angle of one pixel as a whole.

Fig. 3 is a conceptual view of the MVA mode liquid crystal display device. Reference numerals 21 and 22 denote upper and lower glass substrates. Reference numerals 61 and 62 denote protrusive structures formed on these substrates, respectively. Reference numeral 5 denotes liquid crystal molecules. Besides these members, the liquid crystal display further includes transparent electrodes, alignment films, thin film transistors (TFT), phase difference films, and the like, that are not shown in the drawing.

When a liquid crystal material having negative dielectric anisotropy is sealed between two glass substrates, the liquid crystal molecules are aligned substantially vertically by the force of regulation of the alignment film. Pixel electrodes connected to TFT are formed on one of the glass substrates, and a common electrode is formed on the other glass substrate. The protrusive structures are alternately arranged

on the pixel electrodes and on the common electrode.

When TFT is OFF state, the liquid crystal molecules in the gap region between the protrusive structures is aligned in the substantial vertical direction to the interfaces of the substrates, and the liquid crystal molecules in the proximity of each protrusive structure are aligned in the direction vertical to a slope.

When TFT is turned OFF state, an electric field is applied to the liquid crystal, and the liquid crystal molecules are about to turn down from the direction vertical to the substrate. Due to the inclination of the protrusive structures, however, the liquid crystal molecules are regulated to the turn-down direction of the liquid crystal molecules that have turned down from the beginning, so that inclination propagates to the liquid crystal molecules in the gap region.

Fig. 4 shows the inclining direction of the liquid crystal molecules inside one pixel of the MVA mode liquid crystal display device. Reference numerals 61 and 62 denote the protrusive structures disposed on the upper and lower substrates. Reference numeral 7 denotes pixel electrodes disposed on the lower substrate. Each pixel is divided into three longitudinally elongated regions of red, green and blue. The directions of the protrusive structures 61 and 62 are bent 90 degrees inside each pixel.

In this structural example, the gap region of the protrusive structures disposed on the upper and lower substrates is divided into four domains A, B, C and D. The alignment directions of the liquid crystal molecules in each domain are mutually different by 90 degrees. In the MVA mode liquid crystal display device, the liquid crystal molecules are aligned in a plurality of directions when TFT is turned OFF as described above. Therefore, the viewing angle can be broadened.

The MVA mode liquid crystal display device involves

SUMMARY OF THE INVENTION

The object of the present invention is to provide a liquid crystal display device, in particular the MVA mode liquid crystal display device, exhibiting high-speed response characteristic in the whole gradations by simultaneously inclining the alignment of the liquid crystal molecules throughout the whole display regions at the time of the switching operation, and improving the response of the liquid crystal molecules themselves to the electric field.

The object can be attained by a liquid crystal display device which comprises a pair of substrates including a first substrate having pixel electrodes, active devices and an alignment film, and a second substrate having an opposing electrode and an alignment film; and a liquid crystal layer containing nematic liquid crystal molecules and a cured-product formed three-dimensionally of a composition having a liquid crystal skeletal structure, and sandwiched between the pair of substrates; wherein deformation of the liquid crystal layer is at least spray deformation or bend deformation.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 shows an alignment direction of liquid crystal molecules in the present invention;

Fig. 2 shows formation of a photo-cured product.

Fig. 3 is a conceptual view of an MVA mode liquid crystal display device;

Fig. 4 shows a tilt direction of liquid crystal molecules;

Fig. 5 shows inclination propagation of liquid crystal molecules;

Fig. 6 shows dependence of a response time on a

At this time, the force that is to incline the liquid crystal molecules to the alignment direction of the liquid crystal skeletal structure exists. Therefore, switching at a higher speed than under the state where the liquid crystal molecules are inclined and aligned on the interface such as by rubbing means becomes possible.

When the attraction force of the liquid crystal skeletal structure to the liquid crystal molecules is excessively strong, however, the liquid crystal molecules are aligned in the same direction as the liquid crystal skeletal structure and restriction of the inclination at the time of the voltage application becomes so great that characteristics (such as the contrast ratio) are lowered, on the contrary.

In other words, when a mean tilt angle between the liquid crystal skeletal structure and the glass substrate surface in the polar angle direction is α , one of the pre-tilt angles of the liquid crystal molecules on the upper and lower substrate surfaces is β_1 and the other is β_2 , the mean tilt angle of the liquid crystal molecules is θ . The following relation is satisfied:

when no-voltage is applied; and

- (1) When dielectric anisotropy of liquid crystal molecule is negative:

$$\alpha < \theta < (\beta_1 + \beta_2)/2$$

- (2) When dielectric anisotropy of liquid crystal molecule is positive:

$$(\beta_1 + \beta_2)/2 < \theta < \alpha$$

For example, the range is represented by slant line of "without application of voltage" in Fig. 1 when dielectric anisotropy is negative. From the aspects of viewing angle characteristics and response characteristics, it is very important that deformation of the liquid crystal layer during driving is primarily the mode utilizing spray or bent.

At this time, the following condition may be considered. Namely, when a concentration of a photo-cured product of a photo-curing composition having a liquid crystal skeletal structure in the liquid crystal layer is from 0.3 to 3 wt%, a voltage above a threshold voltage is applied to the liquid crystal layer and the tilt angle of the liquid crystal skeletal structure is fixed while the rays of light are being irradiated under the state where the liquid crystal layer is deformed. It is preferred in this case to align the liquid crystal molecules and the liquid crystal skeletal structures so as to satisfy the following relation:

- (3) When dielectric anisotropy of liquid crystal molecule is negative:

$$(\beta_1 + \beta_2)/2 - \theta < \theta - \alpha$$

- (4) When dielectric anisotropy of liquid crystal molecule is positive:

$$0 - (\beta_1 + \beta_2)/2 < \alpha - \theta$$

For example, the range is represented by the slant line of " with application of voltage " in Fig. 1 when dielectric anisotropy is negative. The concentration of the photo-cured product of the photo-curing composition having the liquid crystal skeletal structure is preferably from 0.3 to 3 wt%, most preferably from 1.0 to 2.0 wt%.

Incidentally, the present invention applies the initial inclination not only to the substrate interface but also to the whole bulk of the liquid crystal layer, and can control the inclination to an arbitrary tilt angle. Therefore, the present invention can acquire an improving effect for the system that applies alignment control such as rubbing.

The inventor of this invention has found that a drastic improvement of the response speed by simultaneous inclination of the whole surface can be accomplished by forming the photo-cured product of the photo-curing composition having

the skeletal structure in the liquid crystal layer under the state where the liquid crystal skeletal structure is inclined to the substrates.

In the liquid crystal display device according to the embodiment, 0.3 to 3 wt% of a photo-curing composition having a liquid crystal skeletal structure is added to a nematic liquid crystal layer, and photo-polymerization is carried out to form a photo-cured product while the liquid crystal skeletal structure is kept inclined in a predetermined direction. Deformation of the liquid crystal layer is limited to spray deformation or bend deformation.

In the present embodiment, the liquid crystal skeletal structure imparts a predetermined alignment tilt angle to the liquid crystal molecules in the proximity thereof. Therefore, when a display signal voltage is applied to the liquid crystal layer, the alignment directions are simultaneously aligned throughout the full surface, and the response time can be improved.

In the liquid crystal display device according to the embodiment, substrates for constituting an MVA mode liquid crystal display device have a construction in which transparent pixel electrodes having protrusive structures or slits are formed on the surface of at least one of the substrates, alignment control layers for aligning the major axis direction of the liquid crystal molecules substantially vertically to the substrate surface are disposed on the surface of at least one substrates, and at least one of the alignment control layers is not subjected to alignment treatment.

The liquid crystal display device according to the embodiment stipulates a substrate structure for controlling the liquid crystal layer.

A production method of a liquid crystal display device according to the embodiment stipulates the concentration

of the photo-curing composition so that the major axis direction of the liquid crystal molecules contained in the liquid crystal layer satisfies the following relation with a pre-tilt direction and a polar angle direction of the liquid crystal skeletal structure as other parameters. In other words, when the voltage applied to the liquid crystal layer is 0 V:

When dielectric anisotropy of liquid crystal molecules is negative:

$$\alpha < \theta < (\beta_1 + \beta_2)/2$$

When dielectric anisotropy of liquid crystal molecule is positive:

$$(\beta_1 + \beta_2)/2 < \theta < \alpha$$

Further, when the voltage is applied, there are the following two cases:

When dielectric anisotropy of liquid crystal molecule is negative:

$$(\beta_1 + \beta_2)/2 - \theta < \theta - \alpha$$

When dielectric anisotropy of liquid crystal molecule is positive:

$$\theta - (\beta_1 + \beta_2)/2 < \alpha - \theta$$

The invention according to the embodiment stipulates the condition for determining the concentration of the photo-curing composition so that the tilt angle of the liquid crystal skeletal structures and the tilt angle of the liquid crystal molecules, that varies depending on the amount of the liquid crystal skeletal structures, fall within a predetermined range, and improves the response speed of the liquid crystal molecules throughout the whole display region.

[Example]

To improve the response speed in the MVA mode, it is necessary to make the time required for the propagation of the inclination zero and to simultaneously incline the whole

The first example of the present invention will be given below. Pixel electrodes each having a TFT transistor, and protrusive structures, are formed on one of the substrates. A common electrode and protrusive structures are formed on the other substrate. A liquid crystal monoacrylate monomer UCL-001-K1, a product of Dai-Nippon Ink Co., is added to a liquid crystal MJ-961213, a product of Merck Japan Ltd., and the mixture is charged between two glass substrates. After the mixture is charged, the ultraviolet rays are irradiated while a voltage is being applied. A cured MVA panel is fabricated under the state where the liquid crystal skeletal structure is at about 30 degrees to the substrate surface in the display region.

Here, a polyamic acid material JALS-684, a product of JSR Corp., is used for the alignment film. Protrusive structures having a height of 1.5 μm and a width of 10 μm are formed on both upper and lower substrates with gaps of 37.5 μm among them by using a resist LC-200, a product of Shipley Co. A cell thickness is 4.0 μm .

Fig. 6 shows a measurement result of the response time of the liquid crystal molecules by using the addition amount of the liquid crystal skeletal structure monomer as a parameter. A slight improvement of the response time starts appearing from the addition amount of 0.3 wt% in this graph. It can be also appreciated from the graph that the addition amount of about 1.0 wt% is necessary to strongly restrict the inclination direction on the high voltage side, too. The value starts saturating at about 2.0 wt%.

Fig. 7 shows an absolute transmission factor and contrast relative to the addition amount of the monomer measured simultaneously with the measurement of Fig. 6. In the graph, solid line represents the transmission factor under a bright state (applied voltage: 5.5 V) and under a dark condition (applied voltage: 0 V). Dotted line represents the contrast.

Both transmission factor and contrast keep high values when the addition amount is up to 1.5 wt%, but contrast drops drastically at 2.0 wt%. Almost all liquid crystal molecules are aligned in the direction of the liquid crystal skeletal structure and large scattering is observed at 3.0 wt%.

A low concentration of the liquid crystal monomer (photo-cured product) of from 0.3 to 1.5 wt% may be applied to the application where gradation is of importance and a high concentration of 1.5 to 3.0 wt% may be applied to the fields where the response speed is of importance.

In the second example of the present invention, rubbing treatment is applied to the surfaces of the upper and lower alignment films by using the same liquid crystal material, the same alignment film material and the same monomer material as those of the first example. After the liquid crystal mixture is charged, the ultraviolet rays are irradiated while a voltage is being applied. The liquid crystal mixture is cured when the liquid crystal skeletal structure reaches about 30 degrees relative to the substrate surface in the display region, thereby giving a panel. Here, the addition amount is 2.0 wt% and the rubbing treatment is conducted in the following two ways, that is, rubbing anti-parallel between the upper and lower substrates and rubbing while its direction is deviated by 90 degrees. The cell thickness is 4.0 μm . The result is shown in Fig. 8. The response time is longer in the panel in which rubbing is conducted by deviating the rubbing direction by 90 degrees.

The 90 degrees deviation corresponds to twist deformation, and anti-parallel corresponds to spray deformation. In this way, deformation of the liquid crystal layer is limited to spray or bend other than twist.

The third example of the present invention uses a MVA panel in which materials used, formation condition of the protrusive structures and the cell thickness are the same

as those of the first example. However, the angle of the liquid crystal skeletal structure at the time of curing and the mean tilt angle of the liquid crystal molecules are changed, and the alignment condition and the degree of scattering due to the polymer are examined. Here, the mean tilt angle of the liquid crystal molecules is changed through the addition amount of the monomer, and the angle value is calculated from the transmission at the time of voltage non-application.

Table 1 tabulates the result. Here, $\beta = (\beta_1 + \beta_2)/2$. A good alignment/scattering state can be obtained when the limit angle (β), the tilt angle of the liquid crystal molecules (θ) and the tilt angle of the liquid crystal skeletal structure (α) satisfy the following relation:

$$\beta - \theta < \theta - \alpha$$

When the tilt angle of the liquid crystal molecules departs from the alignment film limit angle and comes close to the tilt angle of the liquid crystal skeletal structure, the alignment/scattering state gets deteriorated. For, when the addition amount of the monomer is increased, scattering by the polymer formed in the cell strongly appears and at the same time, the director of the liquid crystal molecules is disturbed during the formation of the polymer.

[Table 1]

Angles of liquid crystal skeletal structure and liquid crystal molecules, and alignment/scattering condition

β	α	θ	$\beta - \theta < \theta - \alpha$	Alignment	Scattering
90	80	89	<	O	O
90	80	88	<	O	O
90	80	83	>	x	x
90	60	89	<	O	O
90	60	85	<	Δ	Δ
90	60	70	>	x	x
90	30	89	<	O	O
90	30	60	=	x	x
90	30	40	>	x	x

(Note) O: alignment: fair,
scattering: nil

Δ : alignment: rather bad,
scattering: some extent

x: alignment: bad,
scattering: many

The present invention can simultaneously incline the liquid crystal molecules in the display region as a whole, can improve response of the liquid crystal molecules to the electric field and can accomplish extremely high-speed response at all gradations while keeping the excellent alignment condition.